

P – Protection Geotextiles

TenCate Polyfelt® P geotextiles are mechanically bonded (needle punched) continuous filament nonwovens from 100% UV stabilized polypropylene. They have been developed for optimum protection efficiency for geomembranes.

TenCate Polyfelt® P geotextiles maintain the permanent sealing function of synthetic geomembranes

TenCate Polyfelt® P geotextiles prevent direct puncturing of the geomembrane by the sharp edges of the stone fill. Thanks to a combination of product thickness and stiffness, pressure and friction stresses which can damage geomembranes are significantly reduced.

TenCate Polyfelt® P geotextiles offer a high tensile strength at low strain. This supports the protection function as the thickness is maintained even when the geotextile experiences high tensile forces. In addition this takes stress loads from the geomembrane and reduces the danger of sliding especially on slopes.

TenCate Polyfelt® P geotextiles have a drainage function

The high in plane flow of TenCate Polyfelt® P throughout the thickness of the material allows

water and gas to drain. Decades of experience in tunnel construction with this material has shown that TenCate Polyfelt® P replaces the need for drainage material around the tunnel lining.

TenCate Polyfelt® P geotextiles are robust and long-lasting

TenCate Polyfelt® P is resistant to all chemical and biological media usually occurring in soils and construction materials. It cannot be dissolved by water and therefore is harmless to ground water.

TenCate Polyfelt® P geotextiles are equipped with a UV-stabilizer, providing extended resistance to direct sunlight.

Service is a part of quality

Thanks to a worldwide network of subsidiaries and trading partners TenCate Polyfelt® P geotextiles are quickly available. Standard grades can be delivered promptly. For technical questions an experienced team of experts is at your service.



TenCate Polyfelt® P




The advantages at a glance:

- High protection efficiency
- Excellent chemical and biological resistance
- High tensile strength at low elongation
- Good in-plane water and gas permeability




Applications

Landfill surface drainage/sealing



Landfill base sealing




Cut-and-cover tunnels



NATM tunnels



Canals & reservoirs



P – Protection Geotextiles – Technical Data

Properties [Standard]	Unit	P30	P40	P50	P60	P70	P80	P100 S	P120	
Raw material / Type of fibre		100 % polypropylene, UV stabilized, continuous filaments								
Strip tensile strength [EN ISO 10319]	MD/CD kN/m	20/20	27/27	34/34	40/40	43/43	46/46	60/60	75/75	
Elongation at max. load [EN ISO 10319]	MD/CD %	80/70	85/75	85/70	95/78	90/73	95/80	95/80	105/100	
CBR puncture resistance [EN ISO 12236]	kN	3.5	4.5	5.7	6.8	7.5	8.5	10	11	
CBR displacement [EN ISO 12236]	mm	60	60	60	60	60	60	62	63	
Cone drop resistance (hole diameter) [EN ISO 13433]	mm	15	11	9	7.5	7	6	3.9	3	
Protection efficiency [EN 13719 – Deformation at 300 kPa]	%	1.50	1.10	0.80	0.70	0.60	0.55	0.45	0.30	
Opening size [EN ISO 12956]	µm	85	85	80	80	80	75	65	65	
Permeability vertical [EN ISO 11058] Δh = 50 mm	l/m ² s (mm/s)	75	20	45	10	30	10	10	10	
Water flow rate in the plane [EN ISO 12958]	20 kPa 10 ⁶ m ² /s	2.6	3.9	5.5	7.1	9.0	11.0	11.0	11.0	
	100 kPa 10 ⁶ m ² /s	0.7	1.1	1.6	2.3	3.1	4.1	4.1	4.1	
Weathering resistance [EN 12224] Residual strength	%	> 90	> 90	> 90	> 90	> 90	> 90	> 90	> 90	
Exposure time [acc. EN 13249 ff]	days	30	30	30	30	30	30	30	30	
Chemical resistance [EN 14030, Method A] Residual strength	%	100	100	100	100	100	100	100	100	
Microbiological resistance [EN 12225] Residual strength	%	100	100	100	100	100	100	100	100	
Thickness [EN ISO 9863-1]	2 kPa mm	2.8	3.4	4.2	4.5	5.7	6.0	7.2	8.3	
Mass per unit area [EN ISO 9864]	g/m ²	300	400	500	600	700	800	1050	1200	
Forms of Supply										
Width	m	6.0	6.0	6.0	6.0	6.0	6.0	5.4	5.2	
Length	m	110	100	80	65	55	50	40	35	

The values given are average values obtained in our laboratories and in testing institutes. The right is reserved to make changes without notice at any time.

TENCATE GEOSYNTHETICS AUSTRIA GMBH

Schachermayerstr. 18 Tel. +43 732 6983 0, Fax +43 732 5983 5353
A-4021 Linz, Austria service.at@tencate.com, www.tencategeosynthetics.com

BeNeLux Tel. +31 546 544 811 service.nl@tencate.com
Central Eastern Europe Tel. +43 732 6983 0 service.at@tencate.com
Czech Republic Tel. +420 2 2425 1843 service.cz@tencate.com
France | Africa Fax +33 1 34 23 53 48 service.fr@tencate.com
Germany Tel. +40 6074 3751 61 service.de@tencate.com
Italy Tel. +39 0362 34 58 11 service.it@tencate.com
Near Middle East Tel. +971 4810 3295 service.nme@tencate.com

Poland service.pl@tencate.com
Russia | CIS service.ru@tencate.com
Scandinavia | Baltics geonordic@tencate.com
Spain | Portugal service.es@tencate.com
Turkey service.tr@tencate.com
UK | Ireland service.uk@tencate.com

Tel. +48 12 268 8375
Tel. +43 732 6983 0
Tel. +31 546 544 811
Tel. +34 607 499 962
Tel. +43 732 5983 0
Tel. +44 1952 588 066

service.pl@tencate.com
service.ru@tencate.com
geonordic@tencate.com
service.es@tencate.com
service.tr@tencate.com
service.uk@tencate.com



Protective Fabrics
Outdoor Fabrics
Aerospace Composites
Advanced Armour

Geosynthetics
Grass